

Paper for bags, 100% recycled.

Technical characteristics

TEST	STANDARD	DIMENSION	AiaBag											
Nominal basic weight	EN ISO 536	gr/m²	70	75	80	85	90	95	100	110	115	120	125	+−3%
Nominal moisture	EN ISO 287	%	8	8	8	8	8	8	8	8	8	8	8	+−1
Bursting Strength	EN ISO 2758	Kpa m²/g	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	2.0	Indicative
Stretch MD	EN ISO 1924 / 2	%	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4	1.4	−10%
Stretch CD	EN ISO 1924 / 2	%	3	3	3	3	3	3	3	3	3	3	3	−10%
Length strength MD	EN ISO 1924 / 2	m	6200	6200	6200	6200	6200	6200	6200	6200	6200	6200	6200	−10%
Length strength CD	EN ISO 1924 / 2	m	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	2500	−10%
Air resistance (Gurley)	EN ISO 5636-5	S	35	35	35	35	35	35	35	35	35	35	35	Indicative

